P999 EXTRA RIGID

LLDPE cast stretch film mechanically prestretched to very low thickness. Specially indicated where there are light and/or easily deformable goods. Slippery outside and cling inside. ***To be used only on wrapping machines WITHOUT prestretch group or for manual use*.**

Characteristic	Method	Unit	Direction	7 µm	8 µm	9 µm	10 µm	Tolerances
Impact resistance	**ASTM D1709 A**	**g**	**-**	39	41	44	47	10%
Tensile strength at break	**ASTM D882 B**	**MPa**	**Machine Direction**	38	38	39	40	10%
			Transversal Direction	5	5	5,5	5,5	10%
Tensile strength at yield	**ASTM D882 B**	**MPa**	**Machine Direction**	75	76	76	77	10%
			Transversal Direction	20	20	21	21	10%
Elongation at break	**ASTM D882 B**	**%**	**Machine Direction**	130	135	140	145	10%
			Transversal Direction	750	800	825	850	10%
Tear Resistance	**ASTM D1922**	**mN**	**Machine Direction**	1010	1030	1045	1060	10%
			Transversal Direction	2410	2450	2480	2550	10%
Guaranteed Stretch		**%**	**-**	10	15	20	25	5%
Cling		**%**	**-**	125	125	125	125	10%

In case of coloured stretch film these values should be reduced by 10%.
In case of additives these values should be reduced by 5%.

Coloured	AUV 6/12 months	UV Absorber	Antistatic	NetRoll	OxoRoll	Cling Out/In/Both	Printed
✗	✗	✗	✗	✗	✗	✗	✗